

# **BLANK PAGE**



IS 363:1993

भारतीय मानक

(Reaffirmed 1999)

# छपकों और कुंडों की विशिष्टि

( चौथा पुनरीक्षण )

Indian Standard

## HASPS AND STAPLES — SPECIFICATION

( Fourth Revision )

UDC 683.356

© BIS 1993

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

### **FOREWORD**

This Indian Standard was adopted by the Bureau of Indian Standards, after the draft finalized by the Builders Hardware Sectional Committee had been approved by the Civil Engineering Division Council.

This standard was first published in 1951 and subsequently revised in 1961, 1970 and 1976.

This revision of standard makes reference to the latest Indian Standards for various types of matarials specified therein. Consequently, it also indicates the designations for various materials in accordance with the latest versions of these standards. It also incorporates the amendment No. 1 which was issued in 1983.

The committee responsible for the preparation of this standard is given at Annex B.

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test, shall be rounded off in accordance with IS 2: 1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

### Indian Standard

### HASPS AND STAPLES — SPECIFICATION

### ( Fourth Revision )

### 1 SCOPE

This standard covers requirements regarding material, dimensions, manufacture and finish of hasps and staples.

### 2 REFERENCES

The Indian Standard listed in Annex A are necessary adjuncts to this standard.

#### 3 TYPES

Hasps and staples shall be of the following types:

Type	Description						
1	Mild steel, brass or aluminium alloy hasps and staples—safety type (see Fig. 1)						
. 2	Mild steel hasps and staples—wire type ( see Fig. 2 )						

### 4 MATERIAL

Materials used for the manufacture of hasps and staples shall comply with the requirements given in Table 1.


### 5 DIMENSIONS

The leading dimensions of the hasps and staples and tolerances thereon shall conform to those specified in Tables 2 to 4, and Fig. 1 and 2.


Table 1 Requirements for Material for Hasps and Staples

(Clause 4)

SI No.	Material	Suitable Grade in Indian Standard					
(1)	(2)	(3)					
	ttruded aluminium lloy	Designation 63400 WP of IS 733: 1983 or 63 400 WP of IS 1285: 1975					
	uminium alloy neet	52 000-H1 of IS 737: 1986					
iii) C	ast brass	Grade LCB-2 of IS 292: 1983					
iv) M	ild steel	Grade 0 of IS 1079: 1988					
v) M	lild steel wire	½ H of IS 280: 1978					
vi) Ph	nosphor bronze wire	Grade 1 of IS 7608: 1987					
	uminium alloys ars, rods and wire	Designation 63400 WP or 64430 WP of IS 733: 1983 and 64430 WP of IS 739: 1992					



HASP (MILD STEEL BRASS OR ALUMINIUM ALLOY)



D+I+5 mm

D+I+5 mm

C

C

OK+

C-T,

STAPLE
(BRASS OR ALUMINIUM ALLOY!

FIG. 1 MILD STEEL OR BRASS OR ALUMINIUM ALLOY HASPS AND STAPLES (SAFETY TYPE)




Fig. 2 MILD STEEL HASPS AND STAPLES - WIRE TYPE

### **6 MANUFACTURE**

Hasps and staples shall be well made and free from defects. The hinge pin shall be mild steel in the case of mild steel hasps and staples, and of mild steel or brass in the · case of brass or aluminium alloys hasps and staples. The hinge pin in the case of brass hasps and staples may also be of phosphor bronze, if so required by the purchaser. The movement of the hinge shall be free, easy and square, and shall not have play or shake. The hasps shall fit the staple correctly. The staple, except in the case of cast one, shall be riveted properly to its plate. The ends of the hinge pin for the safety type hasps shall be riveted and properly finished. All screw holes shall be clean and countersunk to suit countersunk wood screw of number specified in Tables 2 to 4. All sharp edges and corners shall be removed.

NOTE — In locations susceptible to atmospheric corrosion, use of brass or phospher bronze hinge pins is recommended in the case of brass hasps and staples.

#### 7 FINISH

Unless otherwise specified, hasps and staples shall have finish as given below:

- a) Mild steel hasps Stove enamelled, black and staples
- b) Brass hasps and staples

Oxidized or covered with clear lacquer after polishing as specified by the purchaser

c) Aluminium alloy Anodized (see Note)

NOTE — The quality of anodized finish shall not be less than Grade AC 10 of IS 1868: 1982.

### 8 MARKING

- 8.1 Each hasp and staple shall have marked on it the manufacturer's name or trade-mark.
- **8.1.1** The hasp and staple may also be marked with the Standard Mark.

#### 9 PACKING

Hasps and staples shall be packed in cartons or in other approved packing. Each package shall be labelled with the name or trade-mark of the manufacturer, particulars of the quantity, description of contents, size and type of the hasps and staples.

## 10 SCALE OF SAMPLING AND CRITERION FOR CONFORMITY

#### 10.1 Lot

In any consignment, all the hasps and staples of the same type and size and manufactured at the same time shall be grouped together to constitute a lot.

### 10.2 Lot Size and Sample Size

The number of hasps and staples to be selected from a lot shall depend on the size of the lot and shall be in accordance with col 1 and 2 of Table 5.

10.2.1 The number of hasps and staples to be selected in the sample depends upon the size of the lot and shall be in accordance with col 1 and 2 of Table 5. These hasps and staples shall be selected at random and for this purpose, reference may be made to IS 4905: 1968.

Size	A	B C D E F G H	J	K	R	Thickness of Sheet,	Dia of	Screw Holes								
					of Sheet,	Hinge Pin, d	No. on Hasp	No. on Staple	For Wood Screw No.							
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)	(17)
mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm			
90	90±2	38·0±1·5	46±2	5·00±0·10	5·0±0·5	35·0±1·5	28.0±0.5	8·0±0·5	12±1	8±1	8·0±0·5	2·00±0·10	4·00±0·05	3	4	8
115	$115\pm2$	38·0±1·5	46±2	5·00±0·10	5·0±0·5	55·0±1·5	28 <b>0</b> ±0 5	8·0±0·5	12±1	8±1	8·0±0·5	2·00±0·10	4·00±0·05	3	4	8
150	150±2	45·0±1·5	60±2	6·30±0·10	6·0±0·5	65·0±1·5	33·0±0·5	10 0± <b>0</b> ⋅5	15±1	14±1	9 <b>·</b> 0±0·5	2·24±0·10	5·00±0·06	4	4	10
175	175±2	45·0±1·5	60±2	6·30±0·10	6·0±0·5	65·0±1·5	33·0±0·5	10·0±0·5	15±1	14±1	9 <b>·0</b> ±0·5	2·24±0·10	5·00±0·06	4	4	10

Table 3 Dimensions of Brass or Aluminium Alloy Hasps and Staples — Type 1

(Clauses 5 and 6, and Fig. 1)

Size	A	В	C	D	$\boldsymbol{E}$	$\boldsymbol{F}$	$\boldsymbol{G}$	H	K	R	Thic	kness	Dia of Hinge	Dia of Butt,	S	crew H	oles
											T	$T_i$	Pin, d	$D_1$	No. Hasp on		
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	(13)	(14)	(15)	(16)	(17)	(18)
mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	mm	nım	mm	mm	mm			
90	$90\!\pm\!2$	$40.0 \pm 1.5$	42·0±1·5	5·00±0·25	6·0±0·5	$35\pm1$	28·0±0·5	10·0±0 5	8±1	6·5±0·5	2·00±0·25	3·00±0·25	3·15±0·10	6·0±0·2	3	4	5
115	115±2	40·0±1·5	42·0±1·5	5·00±0·25	6·0±0·5	45±1	28·0±0·5	10·0±0·5	11±1	6·5±0·5	2·00±0·25	3·00±0·25	3·15±0·10	6·0±0·2	3	4	5
150	150±2	46·0±1·5	48·0±1·5	6 00±0·25	7·0±0·5	65±1	32·0±0·5	11·0±0·5	14±1	7·5±0·5	3·00±0·25	4·00±0·25	4·00±0·10	8·0±0·2	4	4	8
175	175±2	46·0±1·5	48·0±1·5	6·00±0·25	7·0±0·5	65±1	32·0±0·5	11·0±0·5	14±1	7·5±0·5	3·00±0·25	4·00±0·25	4·00±0·10	8·0±0·2	4	4	8

Table 4 Dimensions of Mild Steel Hasps and Staples — Type 2

(Clauses 5 and 6, and Fig. 2)

Size	A	· B	C	D	$\boldsymbol{E}$	F	R	Thickness	Screw Holes			
								of Sheet, T	No. on Hasp	No. on Staple	For Wood Screw No.	
(1)	(2)	(3)	(4)	(5)	(6)	(7)	(8)	(9)	(10)	(11)	(12)	
mm	mm	mm	mm	mm	mm	mm	mm	m <b>m</b>				
65	$65{\pm}2$	25·0±1·5	22·0±1·5	$3.15 \pm 0.05$	38·0±1·5	8·0±0·5	5·0±0·5	1·25±0·10	2	2	6	
75	$75\!\pm\!2$	25·0±1·5	$25.0 \pm 1.5$	3·15±0·05	38.0±1.5	8°0±0°5	5·0±0·5	1·25±0·10	2	2	6	
90	90±2	25·0±1·5	$28.0 \pm 1.5$	3·15±0·05	$38.0 \pm 1.5$	8·0±0·5	5·0±0·5	1.25±0.10	2	2	6	
100	$100\!\pm\!2$	32·0±1·5	38·0±1·5	4·00±0·05	42 <sup>.</sup> 0±1 <sup>.</sup> 5	11·0±0·5	6·0±0·5	1·60±0·10	3	2	6	
125	125±2	38 0±1·5	48·0±1·5	5·00±0·06	55·0±1·5	14·0±0·5	7·0±0·5	$1.60 \pm 0.10$	4	4	6	
150	$150\pm2$	45.0±1.5	55·0±1·5	6·30±0·06	55·0±1·5	14·0±0·5	7·0±0·5	2.00±0.10	4	4	10	
175	175±2	50·0±1·5	55·0±1·5	6· <b>3</b> 0±0·06	55·0±1·5	14·0±0·5	8·0±0·5	2·00±0·10	4	4	10	
*V	Vhere so	required b	y the purch	aser, diame	ter may be	5·00±0·05	instead of	$4.00 \pm 0.05$ .				

### 10.3 Tests

All the hasps and staples selected as in 10.2 shall be checked for dimensional requirements (see 5) manufacturing defects (see 6) and finish (see 7). Any hasp and staple which fails to satisfy the requirements of any one or more of the characteristics, shall be considered as defective hasp and staple.

### 10.4 Criterion for Conformity

A lot shall be considered as conforming to the requirements of this standard if the number of defectives found in sample does not exceed the corresponding acceptance number given in col 3 of Table 5, otherwise it shall be considered as

not conforming to the requirements of this standard.

Table 5 Scale of Sampling and Criterion for Acceptance

(Clauses 10.2 and 10.4)

Lot Size	Sample Size	Permissible Number of Defective Hasps and Staples			
(1)	(2)	(3)			
Up to 100	13	0			
101 to 300	20	1			
301 to 500	32	2			
501 to 1 000	50	3			
1 001 and above	ve 80	5			

### ANNEX A

(Clause 2)

### LIST OF REFERRED INDIAN STANDARDS

IS No.	Title	IS No.	Title		
280:1978	Mild steel wire for general engineering purpose (third		general engineering purposes (third revision)		
202 - 1002	revision) Leaded brass ingots and	1079:1988	Hot-rolled carbon steel sheet and strip (fourth revision)		
292:1983	castings (second revision)	1285:1975	Wrought aluminium and		
733 : 1983	Wrought aluminium and aluminium alloy bars, rods and sections for general engineering purposes (third revision)		aluminium alloy extruded round tube and hollow sections (for general engineering purposes) (second revision)		
737:1986	Wrought aluminium and aluminium alloy sheet and	1 <b>868</b> : 198 <b>2</b>	Anodic coatings on aluminium and its alloys (second revision)		
	strip for general engineering	4905:1968	Methods for random sampling		
	purposes (third revision)	7608:1987	Phosphor bronze wire for		
739:1992	Wrought aluminium and aluminium alloy wire for		general engineering purposes (first revision)		

### ANNEX B

( Foreword )

### Builders Hardware Sectional Committee, CED 15

Chairman

SHRI P. KRISHNAN

Representing

Central Public Works Department, New Delhi

Members

SHRI V. K. AGARWAL SHRI A. K. AGARWAL ( Alternate )

SHRI A, BANDOPADHYAY

SHRI GURUSWAMY ( Alternate )
SHRI R. K. BHANDARI

SHRI R. L. SHARMA ( Alternate )

SHRI SUDHIR BATRA CONTROLLER OF STORES

SHRI S. M. GARG

SHRI B. M. GARG ( Alternate )

SHRI A. GHOSH

SHRI A. K. SARKAR ( Alternate )
SHRI N. C. JAIN

LT COL B. PARGHI ( Alternate )

SHRI L. A. JAISINGHANI

SHRI L. K. SINGH (Alternate)
SHRI S. C. KAPOOR
SHRI I. C. KHANNA (Alternate)
SHRI RAM F. KEWALRAMANI

SHRI SURESH CHAND

Col P. C. KHANNA SHRI ANIL CHAND ( Alternate )

SHRI P. ANIL KUMAR
SHRI P. A. KOHLI ( Alternate )

SHRI V. K. MEHTA

SHRI SURAJ PRAKASH ( Alternate )

SHRI J. RAGHURAM

SHRI O. P. RATRA SHRI M. M. MISTRY

SUPTO. ENGINEER

EXECUTIVE ENGINEER ( Alternate )

SHRI SAHIB SINGH VIRDI

SHRI S. MOWIEE (Alternate)
SHRI Y. R. TANEJA, DIRECTOR (CIVIL ENGG)

Hindalco Industries Ltd, Bombay

Northern Region, Ministry of Industry, New Delhi

Delhi Development Authority, New Delhi

Mech (India) Industries, Delhi Railway Board (Ministry of Railways)

D. P. Garg & Co, NOIDA

National Test House, Calcutta

Ministry of Defence, New Delhi

Fixopan Engineers Pvt Ltd, New Delhi

Directorate General of Supplies & Disposals, New Delhi

Indian Institute of Architects, Bombay

Central Building Research Institute (CSIR), Roorkee

Argent Industries, New Delhi

Indian Aluminium Co Ltd, Calcutta

Engineer-in-Chief's Branch, Army Headquarters, New Delhi

J. H. Aluminium Pvt Ltd, Madras

Building Material & Technology Promotion Council, New Delhi National Building Organization, New Delhi

Tamil Nadu Housing Board, Madras

M. C. Mowjee & Co Pvt Ltd, Calcutta

Director General BIS ( Ex-officio Member )

Member Secretary HEMANT KUMAR Joint Director (Civ Engg) BIS

### Standard Mark

The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

### Bureau of Indian Standards

BIS is a statutory institution established under the Bureau of Indian Standards Act, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, types or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards Monthly Additions'. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc: No. CED 15 (5260)

Amend No.

### Amendments Issued Since Publication

Date of Issue

	240 0, 15540	Text Affected
<del></del>		
	BUREAU OF INDIAN STANDARDS	
Headquarters: Manak Bhavan, 9 Bahadur S Telephones: 331 01 31, 331	Shah Zafar Marg, New Delhi 110002 13 75	Telegrams: Manaksanstha (Common to all Offices)
Regional Offices:		Telephone
Central: Manak Bhavan, 9 NEW DELHI 1100		{331 01 31 331 13 75
Eastern: 1/14 C. I. T. Schen CALCUTTA 7000	ne VII M, V. I. P. Road, Maniktola 54	{37 84 99, 37 85 61 37 86 26, 37 86 62
Northern: SCO 445-446, Sec	ctor 35-C, CHANDIGARH 160036	{53 38 43, 53 16 40 53 23 84
Southern: C. I. T. Campus,	IV Cross Road, MADRAS 600113	{235 02 16, 235 04 42 235 15 19, 235 23 15
Western: Manakalaya, E9 M BOMBAY 400093	MIDC, Marol, Andheri (East)	\[ \begin{cases} 632 & 92 & 95, & 632 & 78 & 58 \\ 632 & 78 & 91, & 632 & 78 & 92 \end{cases} \]

Branches: AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR.

LUCKNOW, PATNA, THIRUVANANTHAPURAM.

Text Affected